

AD-A182 211

A PULSED FIELD GRADIENT NUCLEAR MAGNETIC RESONANCE
SPECTROMETER FOR DIREC (U) NORTHWESTERN UNIV EVANSTON
IL D H WHITMORE 24 APR 87 AFOSR-TR-87-8847

1/1

UNCLASSIFIED

AFOSR-85-0098

F/G 7/4

NL

END
8-87
DTIC



PHOTOCOPY RESOLUTION TEST CHART

UNCLASSIFIED
SECURITY CLASSIFICATION OF THIS PAGE

DTIC FILE COPY ②

REPORT DOCUMENTATION PAGE

1a. REPORT SECURITY CLASSIFICATION Unclassified			1b. RESTRICTIVE MARKINGS		
2a. SECURITY CLASSIFICATION AUTHORITY 21			3. DISTRIBUTION/AVAILABILITY OF REPORT Approved for public release; Distribution unlimited		
4. AD-A182 211			5. MONITORING ORGANIZATION REPORT NUMBER(S) AFOSR-TR- 87 - 0847		
6a. NAME OF PERFORMING ORGANIZATION Northwestern University		6b. OFFICE SYMBOL (if applicable)	7a. NAME OF MONITORING ORGANIZATION AFOSR/NC		
6c. ADDRESS (City, State, and ZIP Code) 619 Clark Street Evanston, Illinois 60201			7b. ADDRESS (City, State, and ZIP Code) Building 410 Bolling AFB, D.C. 20332-6448		
8a. NAME OF FUNDING / SPONSORING ORGANIZATION AFOSR		8b. OFFICE SYMBOL (if applicable) NC	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER AFOSR-85-0098		
8c. ADDRESS (City, State, and ZIP Code) Building 410 Bolling AFB, D.C. 20332-6448			10. SOURCE OF FUNDING NUMBERS		
			PROGRAM ELEMENT NO 61102F	PROJECT NO 2917	TASK NO A2
			WORK UNIT ACCESSION NO		
11. TITLE (Include Security Classification) A Pulsed Field Gradient Nuclear Magnetic Resonance Spectrometer for Direct Measurement of Ionic Diffusion in Solid Electrolytes.					
12. PERSONAL AUTHOR(S) Whitmore, Donald Herbert					
13a. TYPE OF REPORT Final Technical Report		13b. TIME COVERED FROM 1-1-1985 TO 12-31 1986		14. DATE OF REPORT (Year, Month, Day) April 24, 1987	
15. PAGE COUNT 3					
16. SUPPLEMENTARY NOTATION					
17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)		
FIELD	GROUP	SUB-GROUP	NMR, Spectrometer, Diffusion, Ions, Solid Electrolytes.		
19. ABSTRACT (Continue on reverse if necessary and identify by block number) A pulsed field gradient nuclear magnetic resonance spectrometer was successfully constructed which is based on a superconducting magnet and has magic-angle spinning capabilities. A dewar facility is an integral part of this system so as to permit investigation of ionic diffusion down to 77°K, along with a sample heating arrangement for diffusion measurements up to 300°C. This spectrometer has been employed in the measurements of protonic diffusion coefficients in γ -alumina solid electrolytes and cation, anion and self-diffusion coefficients in amorphous polymeric electrolytes.					
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT <input checked="" type="checkbox"/> UNCLASSIFIED/UNLIMITED <input checked="" type="checkbox"/> SAME AS RPT <input type="checkbox"/> DTIC USERS			21. ABSTRACT SECURITY CLASSIFICATION Unclassified		
22a. NAME OF RESPONSIBLE INDIVIDUAL Dr. John Wilkes			22b. TELEPHONE (Include Area Code) (202) 767-4960		22c. OFFICE SYMBOL NC

DTIC
ELECTE
JUL 02 1987
E

62 117

AFOSR-TR- 87 - 0 84 7

AIR FORCE OFFICE OF SCIENTIFIC RESEARCH

Final Technical Report

on

Grant No. AFOSR-85-0098

**A Pulsed Field Gradient Nuclear Magnetic
Resonance Spectrometer for Direct Measurement
of Ionic Diffusion in Solid Electrolytes**

Principal Investigator

**Donald H. Whitmore
Northwestern University
Evanston, Illinois 60201**

Accession For	
NTIS GRA&I	<input checked="checked" type="checkbox"/>
DTIC TAB	<input checked="checked" type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

April 1987



Final Technical Report on Grant No. AFOSR-85-0098

We have successfully designed and constructed a working NMR pulsed field gradient (PFG) spin-echo spectrometer system for the direct observation of ion diffusivities in solid and amorphous electrolytes. A dedicated part of this system is a large-bore superconducting magnet installed in a low-loss helium dewar which was available for this purpose in Northwestern's Materials Research Center NMR Facility Laboratory. The moderate field of 40 KOe provided by this magnet represents a compromise between the needed working volume (a 4-inch diameter room-temperature bore) to accommodate pulse field gradient NMR apparatus and the requisite field strength to improve sensitivity. An inert gas flow cryostat furnace, designed for high-resolution NMR magnets by Oxford Instruments, is an integral part of our system; this unit includes controllers and transfer lines and permits measurements to be made over the temperature range from 77 to 600K.

The pulsed spectrometer electronics used in this new system were patterned after an earlier circuit design originated at Northwestern University [Gibson et al., Rev. Sci. Instr. 52, 1509 (1981)], but was complemented by a high-power, wide-band transmitter and a dedicated microcomputer for signal averaging. The pulsed field gradient electronics and the pulsing unit, constructed in our electronics shop following the original circuit design of Karlicek and Lowe [J. Mag. Resonance 37, 75 (1980)], allows gradient fields of 10 Oe/cm which is suitable for our new system.

An important advance in techniques for the direct observation of diffusion coefficients in solids and liquids results from a combination of coherent averaging NMR methods and the pulsed field gradient approach. In principle, the most powerful of these averaging methods is that of magic-angle spinning (MAS), a capability which we have incorporated into our PFG

spectrometer system. Our MAS probe is a custom-made unit with variable temperature capability which allows multifrequency solid-state NMR and permits relaxation measurements to be accomplished on less sensitive nuclei such as nitrogen in the fast proton conducting electrolyte ammonium hydronium β'' -alumina.

Using our new PEG spectrometer, we have to-date made diffusion coefficient measurements on: (a) some amorphous polymer electrolytes (D_{Li} and D_p in polyethylene oxide/ $LiCF_3SO_3$ complexes); (b) protonic ammonium/hydronium β'' -alumina and hydrogen uranyl glasses ($H_{5n-2}UO_2(IO_6)_n \cdot nH_2O$).

END

8-87

DTIC